

TUFFLEX® PLUS

Tufflex® Plus offers a high strength to weight ratio and is an excellent replacement for heavier copolymer lines. It's unique blend of polyester and copolymer in each strand makes for a highly efficient construction. Tufflex Plus is torque balanced, has excellent wear resistance, and is one of the quickest ropes to splice.

Tufflex Plus is an excellent choice as mooring, tie-up and pendant lines, tug assist lines and for general purpose heavy marine applications.

Features & Benefits

- Moderate stretch
- Torque free
- Easy splicing
- Soft hand
- Excellent abrasion resistance
- Floats

Applications

- Vessel mooring lines
- Tug assist lines
- General purpose heavy marine applications

Type approved product

CERTIFIED BY DNV MARITIME

MEG4 APPROVED

OCIMF

Size Dia.		Line Linear Density (LLD)	Weight	Minimum Break Force		Line Design Break Force (LDBF)	
				Unspliced		Spliced	
inch	mm	kg/m	kg/ 220m	Ton	kN	Ton	kN
1	24	0.39	84.7	14.8	145	13.3	130
1-1/16	26	0.45	99	17.4	171	15.7	154
1-1/4	28	0.52	114.4	20.1	197	18.1	177
1-3/16	30	0.60	131.1	23.1	226	20.8	204
1-5/16	32	0.68	149	26.3	258	23.7	232
1-3/8	34	0.74	163	29.6	290	26.6	261
1-1/2	36	0.80	176	33.0	324	29.7	291
1-9/16	38	0.89	196	37.7	370	33.9	332
1-5/8	40	0.98	216	42.9	421	38.6	378
1-11/16	42	1.08	238	47.2	463	42.5	417
1-3/4	44	1.19	262	51.8	508	46.6	457
2	48	1.41	310	62.0	608	55.8	547
2-1/8	52	1.66	365	73.4	720	66.1	648
2-5/16	56	1.92	422	84.6	829	76.1	746
2-3/8	58	2.06	453	87.4	857	78.7	772
2-1/2	60	2.21	486	95.8	939	86.2	845
2-5/8	64	2.51	552	107.8	1057	97.0	951
2-3/4	68	2.83	623	122.1	1197	109.9	1077
3	72	3.18	700	137.4	1347	123.7	1213
3-1/8	76	3.54	779	152.1	1491	136.9	1342
3-1/4	80	3.92	862	167.4	1641	150.7	1477
3-5/16	84	4.32	951	181.2	1776	163.1	1599
3-5/8	88	4.75	1045	195.0	1912	175.5	1721
3-3/4	92	5.19	1142	212.2	2080	191.0	1873
4	96	5.65	1243	230.0	2255	207.0	2029
4-1/8	100	6.13	1349	249.6	2447	224.6	2202
4-1/4	104	6.63	1459	270.0	2647	243.0	2382


Tensile Strengths are determined in accordance with Cordage Institute 1500, Test Methods for Fiber Rope. Weights are calculated at linear density under standard preload (200d²) plus 5%. Additional sizes available upon request. Please visit cortlandinternational.com or contact your sales representative for full product data sheets.

Technical Information

Specific gravity	**0.98***
Melting point	**329°F (165°C)**
Critical temp.	**140°F (60°C)**
Coefficient of friction	**0.12–0.15***
Elongation at break	**15–20%**
Fiber water absorption	**0–1%**
UV resistance	**good**
Wet abrasion	**good**
Dry abrasion	**good**

* value based on data supplied by the fiber manufacturer for new, dry fiber

Tufflex Plus Elongation (%)



CORTLAND INTERNATIONAL™

TUFFLEX® PLUS

Rope Specifications

Minimum Tensile Strength Minimum tensile strengths shown are for new (unused) rope and will decrease after use. All tests are performed in accordance with Cordage Institute Standard CI 1500-2. The rope strength will be reduced after use due to heat, abrasion, ultraviolet or chemical exposure. The tensile strengths may be further reduced by up to 50% as a result of knots or kinks. Minimum tensile strengths are defined as two standard deviations (typical about 10%) below the average.

Maximum Working Loads Maximum working loads are determined by dividing the tensile strength by the safety factor. The safety factor is a function of the physical properties of the rope, the age and history of the rope, the type of service it will be subjected to and the risks involved if failure occurs. For a rope manufacturer to give blanket working load recommendations would be like a car manufacturer giving the "safe driving speed" of their cars. Obviously the conditions of use far outweigh the design characteristics of the rope. Typically safety factors vary from 3:1 (for new rope used in applications with uniform loading and where failure would cause little or no risk to equipment or personnel) to 20:1 (for conditions involving moderate shock loading, possibility of snags or kinks or where failure could cause severe risk to equipment or personnel).

Rope Weights Rope weights shown are average and may vary plus or minus 5%.

Working Elongation Working elongation is shown from a preload tension of 200 times the diameter squared per the Cordage Institute Standard.

Special Requirements

Factory Splicing Various types are available for all of our ropes. Splices can be provided with various types of chafe protection or coatings.

Custom Lengths Special constructions are available on request.

Rope Terminations Cortland International can provide custom terminations such as thimbles, links, rings and custom hardware. Terminations are available in plastic, bronze, stainless steel and galvanized steel. Please call, or email your requirements to contact@cortlandinternational.com for a quotation.

Special Coatings Coatings such as polyurethane, polyethylene and vinylesters may be applied to any of the synthetic ropes to improve snag resistance, sunlight resistance or for color coding. Cortland can provide ropes with a variety of finishes to meet your needs.

Commercial and Military Specifications Certificates of compliance are supplied at no charge if requested when placing the order. Certified test reports can be provided at an additional charge when requested at the time of the order.

CORTLAND INTERNATIONAL™