

POLYESTER 12- AND 12X12 PLAIT

Polyester 12- and 12x12 Plait provides high strength, low stretch and excellent abrasion resistance in a unique single braid construction.

This construction is easily spliced using a standard tuck splice and is 30% stronger than three strand or 8 plait polyester. Its torque free braided construction provides easy handling and prevents kinks and hockles.

Polyester 12- and 12x12 Plait is delivered standard with an overlay marine finish and a spliceable polyurethane finish in clear. Other colors are available upon request.

Features & Benefits

- Low stretch
- High strength
- Soft hand
- Torque free
- Easy splicing
- Meets MIL-R-24750

Applications

- Tug working lines
- Mooring pendants
- Shock lines

Type approved product



Nominal Diameter		Size (circ in.)	Approximate Weight		Minimum Tensile Strength Spliced Rope		Minimum Tensile Strength ISO Unspliced Rope	
inch	mm		lbs/100ft	kg/100m	lbs	MT (tonnes)	lbs	MT (tonnes)
12 Plait								
5/8	16	2	12.2	18.1	12,100	5.5	13,400	6.1
3/4	18	2-1/4	15.9	23.6	15,800	7.2	17,600	8.0
7/8	22	2-3/4	26.3	39.1	24,200	11.0	26,900	12.2
1	24	3	33.0	49.1	27,500	12.5	30,600	13.9
1-1/8	28	3-1/2	39.7	59.1	35,500	16.1	39,400	17.9
12x12 Plait								
1-1/4	30	3-3/4	50.6	75.3	42,100	19.1	46,800	21.2
1-5/16	32	4	58.7	87.3	48,200	21.9	53,600	24.3
1-1/2	36	4-1/2	66.8	99.4	59,600	27.0	66,200	30.0
1-5/8	40	5	84.1	125.1	72,200	32.8	80,200	36.4
1-3/4	44	5-1/2	96.0	142.8	84,400	38.3	93,800	42.6
2	48	6	121.9	181.3	101,000	45.8	112,200	50.9
2-1/8	52	6-1/2	138.6	206.3	119,000	54.0	132,200	60.0
2-1/4	56	7	155.8	231.9	137,000	62.2	152,200	69.1
2-1/2	60	7-1/2	185.9	276.6	163,000	74.0	181,100	82.2
2-5/8	64	8	212.9	316.7	179,000	81.2	198,900	90.2
2-3/4	68	8-1/2	244.9	364.4	202,000	91.7	224,400	101.8
3	72	9	267.4	397.8	233,000	105.7	258,900	117.5
3-1/4	80	10	325.3	484.0	282,000	127.9	313,300	142.2
3-1/2	84	10-1/2	389.5	579.6	322,000	146.0	357,800	162.0
3-5/8	88	11	398.4	592.9	340,000	154.3	377,800	171.4
4	96	12	505.9	752.7	409,000	185.6	454,400	206.2
4-1/8	104	12-1/2	541.0	805.1	444,000	201.0	493,300	224.0
4-1/4	108	13	585.9	871.9	467,000	212.0	518,900	235.0


Tensile Strengths are determined in accordance with Cordage Institute 1500, Test Methods for Fiber Rope. Weights are calculated at linear density under standard preload (200d²) plus 5%. See reverse side for application and safety information.

Technical Information

Specific gravity	1.38*
Melting point	482°F (250°C)
Critical temp.	350°F (177°C)
Coefficient of friction	0.12–0.15*
Elongation at break	15–20%
Fiber water absorption	0–1%
UV resistance	excellent
Wet abrasion	excellent
Dry abrasion	excellent

* value based on data supplied by the fiber manufacturer for new, dry fiber

Polyester 12- and 12x12 Plait Elongation (%)



POLYESTER 12- AND 12X12 PLAIT

Rope Specifications

Minimum Tensile Strength Minimum tensile strengths shown are for new (unused) rope and will decrease after use. All tests are performed in accordance with Cordage Institute Standard CI 1500-02. The rope strength will be reduced after use due to heat, abrasion, ultraviolet or chemical exposure. The tensile strengths may be further reduced by up to 50% as a result of knots or kinks. Minimum tensile strengths are defined as two standard deviations (typical about 10%) below the average.

Maximum Working Loads Maximum working loads are determined by dividing the tensile strength by the safety factor. The safety factor is a function of the physical properties of the rope, the age and history of the rope, the type of service it will be subjected to and the risks involved if failure occurs. For a rope manufacturer to give blanket working load recommendations would be like a car manufacturer giving the "safe driving speed" of their cars. Obviously the conditions of use far outweigh the design characteristics of the rope. Typically safety factors vary from 3:1 (for new rope used in applications with uniform loading and where failure would cause little or no risk to equipment or personnel) to 20:1 (for conditions involving moderate shock loading, possibility of snags or kinks or where failure could cause severe risk to equipment or personnel).

Rope Weights Rope weights shown are average and may vary plus or minus 5%.

Working Elongation Working elongation is shown from a preload tension of 200 times the diameter squared per the Cordage Institute Standard.

Special Requirements

Factory Splicing Various types are available for all of our ropes. Splices can be provided with various types of chafe protection or coatings.

Custom Lengths Special constructions are available on request.

Rope Terminations Cortland International can provide custom terminations such as thimbles, links, rings and custom hardware. Terminations are available in plastic, bronze, stainless steel and galvanized steel. Please call, or email your requirements to contact@cortlandinternational.com for a quotation.

Special Coatings Coatings such as polyurethane, polyethylene and vinylesters may be applied to any of the synthetic ropes to improve snag resistance, sunlight resistance or for color coding. Cortland can provide ropes with a variety of finishes to meet your needs.

Commercial and Military Specifications Certificates of compliance are supplied at no charge if requested when placing the order. Certified test reports can be provided at an additional charge when requested at the time of the order.